

PROPERTIES	
<b>Fibre</b>	<b>Coir - straw</b>
Fibre Content	50% – 50%
Fibre Characteristics	untreated, natural
<b>Weight / Total</b>	<b>~ 800 g/m<sup>2</sup> +/- 10%</b>
Weight / Fibre	~ 450 g/m <sup>2</sup>
Blanket Thickness	8 – 15 mm
Functional Longevity	18 – 24 months
Functional Longevity Wire Mesh	approx. 12-15 years
Bottom Netting Type	Light – PP
Bottom Netting Mesh Size	6 x 6 mm
Bottom Netting Weight	4,8 g/m <sup>2</sup>
Inner Netting Type	Medium - PP
Inner Netting Mesh Size	12 x 13 mm
Inner Netting Weight	7,1 g/m <sup>2</sup>
Stitching thread	PP-thread (brown), UV-degradable
Stitching thread tensile strength	6,5 cN/dtex
Slope recommendation	max. 65°
STANDARDS	
Tensile Strength EN ISO-10319	89,5 kg-force per 25cm
Type	<b>acc. to DIN 1200</b> – 0,8 mm wire
Size	25 x 25 mm, hexagon
Weight	350 g/m <sup>2</sup>
Galvanized Coating	+/- 0,075 mm
Break Resistance	350 – 500 N/mm <sup>2</sup>
SHIPPING & ORDER INFORMATION	
<b>Part No.</b>	<b>O5D120</b>
Width	1,20 m
Length	25 m
Area per Roll	30 m <sup>2</sup>
Weight per Roll	30 kg
Diameter per Roll	0,38 m
Volume per Roll	0,17 m <sup>3</sup>

We cannot warrant our products to perform under unlimited circumstances due variables such as soil conditions, manner of installation and particularly severe weather conditions. Satisfactory results may not meet your expectations. No one can guarantee that required moisture will occur to permit growth after seed germination. We will not be liable for damages or losses, direct or indirect, of our GREENFIX Range of Products due to the above reasons.

Latest-Update: May 8, 2017

Name: Kai Tietjen

File Name: ROCKMAT 5D

Copyright of these GREENFIX Document is reserved by SOILTEC GmbH. Copying or transmission of these document in whole or in part or any information contained therein is strictly prohibited without the prior authorization of SOILTEC GmbH, Germany.